

TF9AAA (FC/HE/tl Series)
THERMOLAST® K
Applications with food contact; excellent elastic properties, translucent
Typical applications

- Closures
- Flexible Connections
- Household articles
- Membranes
- Packaging (for food and careproducts)
- Seals
- Valves

Material advantages

- Applications with food contact
- Easy coloring(compounds in natural colors)
- EN71/3
- Excellent mechanical properties
- FDA compliant
- Halogen-free
- High resilience
- Perfect adhesion to PP
- Regulation (EU) 10/2011

Processing Method: Extrusion, Injection Molding

Product properties

Compound name	TF9AAA
Series	FC/HE/tl
Color	transparent

Mechanical properties

Hardness Shore A	83 ShoreA	DIN ISO 7619
Density	0.890 g/cm ³	DIN EN ISO 1183-1
Tensile Strength ¹	20.5 MPa	DIN 53504 / ISO 37
Elong. at Break S2 ¹	700 %	DIN 53504 / ISO 37
Tear Resistance ¹	30.0 N/mm	DIN ISO 34-1
Compr. Set 72h/RT	29 %	DIN ISO 815
Compr. Set 24h/70°C	41 %	DIN ISO 815
Compr. Set 24h/100°C	70 %	DIN ISO 815

¹ Deviating from ISO 37 standard test piece S2 is tested with a traverse speed of 200 mm/min.

All values published in this data sheet are rounded average values.
Specification limits are based on three-fold standard deviation from the average value.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.

TF9AAA (FC/HE/tl Series)
THERMOLAST® K
Processing Guideline Extrusion

Cylinder temperature	160 - 180 - 200 °C; max. 230 °C (320 - 356 - 392 °F; max. 446 °F).
Screw geometry	Standard three-zone screw (e.g. polyolefin screw). The screw must be able to provide sufficient shearing.
L/D ratio	At least 25
Compression ratio	At least 3.5 : 1
Screens / breaker plate	A breaker plate and a screen pack are generally recommended in the extruder configuration in order to increase pressure.
Die land	3 - 5 mm (0,12 - 0,16 in.)
Extruder Head	Ca. 180 °C (355 °F)
Die temperature	Ca. 190 - 180 °C (374 - 410 °F)
Pre drying	Pre drying of the material is not necessary; if surface moisture forms as a result of changes in temperature, the material should be dried for 2 - 4 hours at 60 - 80 °C (140 - 175 °F).
Calibration	Generally not necessary; support elements may be required when extruding THERMOLAST® compounds with high hardness or when coextruding with standard thermoplastics.

Processing Guideline Injection Molding

Cylinder temperature	220 - 200 - 180 °C max. 250 °C (428 - 392 - 356 °F, max. 482 °F)
Hotrunner	Hot runner temperatures: 200 -250 °C (390 - 480 °F). The runner should be empty after a maximum of 2 - 3 shots.
Injection pressure	200 - 1000 bar (2900 - 14504 psi) (depending on the size and weight of the part).
Injection rate	In general, the fill time should not be more than 1–2 seconds.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.

TF9AAA (FC/HE/tl Series)

THERMOLAST® K

Processing Guideline Injection Molding

Hold pressure	We recommend to derive the optimum hold pressure from determining the solidification point, starting with 40 % - 60 % of the required injection pressure.
Back pressure	20 - 50 bar (285 - 710 psi); if colour batches are used, higher back pressure is necessary.
Screw retraction	If an open nozzle is used processing with screw retraction is advisable.
Mold temperature	25 - 40 °C (77 - 104 °F)
Pre drying	Pre drying of the material is not necessary; if surface moisture forms as a result of changes in temperature, the material should be dried for 2 - 4 hours at 60 - 80 °C (140 - 175 °F).
Needle valve	With materials < 50 Shore A the use of a needle seal nozzle is advisable.
Screw geometry	Standard 3-zone polyolefine screw.
Residence time	The residence time is to be set as short as possible with a maximum of 10 minutes.
Cleaning recommendation	For cleaning and purging of the machine it is appropriate to use polypropylene or polyethylene. Machine must be PVC-free.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.