



# Sarlink® TPV 3170

## Teknor Apex Company - Thermoplastic Vulcanizate

Thursday, January 31, 2019

### General Information

#### Product Description

SARLINK® TPV 3100 series are engineered materials designed primarily for general purpose, automotive and industrial applications requiring a good balance of thermal, mechanical, and physical properties. SARLINK® 3170, available in NAT and BLK, is a medium hardness, low density, multi-purpose thermoplastic vulcanizate that can be processed by injection molding, blow molding or extrusion for applications such as grips, seals, gaskets, profiles, hose & tubes, bellows, and other articles.

#### General

Material Status	• Commercial: Active		
Features	<ul style="list-style-type: none"> <li>• Bondability</li> <li>• Chemical Resistant</li> <li>• General Purpose</li> <li>• Good Adhesion</li> <li>• Good Flexibility</li> </ul>	<ul style="list-style-type: none"> <li>• Good Moldability</li> <li>• Good Processability</li> <li>• Good Surface Finish</li> <li>• High Elasticity</li> <li>• Low Density</li> </ul>	<ul style="list-style-type: none"> <li>• Medium Hardness</li> <li>• Medium Heat Resistance</li> <li>• Resilient</li> <li>• Weather Resistant</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Appliance Components</li> <li>• Automotive Applications</li> <li>• Automotive Exterior Parts</li> <li>• Automotive Interior Parts</li> <li>• Automotive Under the Hood</li> <li>• Blow Molding Applications</li> </ul>	<ul style="list-style-type: none"> <li>• Gaskets</li> <li>• General Purpose</li> <li>• Handles</li> <li>• Hose</li> <li>• Industrial Applications</li> <li>• O-rings</li> </ul>	<ul style="list-style-type: none"> <li>• Pipe Seals</li> <li>• Profiles</li> <li>• Rubber Replacement</li> <li>• Seals</li> <li>• Tubing</li> </ul>
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
UL File Number	• QMFZ2.E54709		
Appearance	• Black	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

### ASTM and ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.948	g/cm <sup>3</sup>	ASTM D792
Density	0.950	g/cm <sup>3</sup>	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	3.30	MPa	
Flow : 100% Strain	5.10	MPa	
Tensile Stress			ISO 37
Across Flow : 100% Strain	3.30	MPa	
Flow : 100% Strain	5.10	MPa	
Tensile Strength			ASTM D412
Across Flow : Break	7.72	MPa	
Flow : Break	6.70	MPa	
Tensile Stress			ISO 37
Across Flow : Break	7.70	MPa	
Flow : Break	6.70	MPa	

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# Sarlink® TPV 3170

## Teknor Apex Company - Thermoplastic Vulcanizate

<b>Elastomers</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Elongation			ASTM D412
Across Flow : Break	670	%	
Flow : Break	300	%	
Tensile Elongation			ISO 37
Across Flow : Break	670	%	
Flow : Break	300	%	
Tear Strength - Across Flow	42.0	kN/m	ASTM D624
Tear Strength - Across Flow <sup>2</sup>	42	kN/m	ISO 34-1
Compression Set			ASTM D395
23°C, 22 hr	25	%	
70°C, 22 hr	43	%	
125°C, 70 hr	63	%	
Compression Set			ISO 815
23°C, 22 hr	25	%	
70°C, 22 hr	43	%	
125°C, 70 hr	63	%	
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	71		
Shore A, 5 sec, Injection Molded	75		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	71		
Shore A, 5 sec, Injection Molded	75		
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
<b>Aging</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Change in Tensile Strength in Air - Across Flow			ASTM D573
135°C, 1000 hr	-8.0	%	
100% Strain, 135°C, 1000 hr	10	%	
150°C, 168 hr	-4.0	%	
100% Strain, 150°C, 168 hr	5.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
135°C, 1000 hr	-8.0	%	
100% Strain 135°C, 1000 hr	10	%	
150°C, 168 hr	-4.0	%	
100% Strain 150°C, 168 hr	5.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
135°C, 1000 hr	-13	%	
150°C, 168 hr	-14	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
135°C, 1000 hr	-13	%	
150°C, 168 hr	-14	%	
Change in Durometer Hardness in Air			ASTM D573
Shore A, 135°C, 1000 hr	-1.0		
Shore A, 150°C, 168 hr	3.0		

# Sarlink® TPV 3170

## Teknor Apex Company - Thermoplastic Vulcanizate

Aging	Nominal Value	Unit	Test Method
Change in Shore Hardness in Air			ISO 188
Shore A, 135°C, 1000 hr	-1.0		
Shore A, 150°C, 168 hr	3.0		
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	120	%	ASTM D471
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	120	%	ISO 1817
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm, Natural and Black Colors)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary, @ 206/s			
200°C	290	Pa·s	ISO 11443
200°C	290	Pa·s	ASTM D3835

### Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	180 to 215	°C
Middle Temperature	180 to 215	°C
Front Temperature	180 to 215	°C
Nozzle Temperature	187 to 220	°C
Processing (Melt) Temp	185 to 220	°C
Mold Temperature	10 to 55	°C
Back Pressure	0.100 to 1.00	MPa
Screw Speed	100 to 200	rpm
Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	180 to 200	°C
Cylinder Zone 2 Temp.	180 to 205	°C
Cylinder Zone 3 Temp.	187 to 210	°C
Cylinder Zone 4 Temp.	187 to 210	°C
Melt Temperature	195 to 215	°C
Die Temperature	195 to 215	°C
Take-Off Roll	20 to 50	°C

### Extrusion Notes

Screen Pack: 20 to 60 mesh  
Screw: general purpose  
Compression Ratio: 3:1

# Sarlink® TPV 3170

## Teknor Apex Company - Thermoplastic Vulcanizate

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Method Ba, Angle (Unnicked)

---